

# T E S T C E R T I F I C A T E

ST-25-08-18-02

**Product:** Laminate flooring: "Çamsan Original"  
Thickness: 8,0 mm

**Producer:** Çamsan Ordu Ağaç Sanayi ve Ticaret Anonim Şirketi  
Kökenli Mah. Sivas Yolu Çamsan Fırınlar Mücavir Sokak  
No: 1 PK: 35  
Altınordu / ORDU  
Türkiye

**Order:** Determination of Laminate Flooring Topical Moisture Resistance according to NALFA-Method and evaluation for an extended **72 h** water exposure

**Test report:** 2724320

**Test results:**

Parameter		Wet Swell (informative only)	Re-dry Swell / Rating	Requirements according NALFA for 24 h
Final Thickness Swell [mm]	Position 1	0,53	0,23	Not applicable
	Position 2-4	0,32	<b>0,11</b>	
Qualitative Rating Specimen 1/2		4/4	<b>2/1</b>	<b>Fulfilled</b>
Water Leakage		<b>Not detected</b>		

Dresden, 18/08/2025

*Adrian Mischak*

Head of laboratory



*P.P. Weide*

Engineer in charge