

T E S T C E R T I F I C A T E

ST-25-08-18-02

Product: Laminate flooring: "Çamsan Original"
Thickness: 8,0 mm

Producer: Çamsan Ordu Ağaç Sanayi ve Ticaret Anonim Şirketi
Kökenli Mah. Sivas Yolu Çamsan Fırınlar Mücavir Sokak
No: 1 PK: 35
Altınordu / ORDU
Türkiye

Order: Determination of Laminate Flooring Topical Moisture Resistance according to NALFA-Method and evaluation for an extended 72 h water exposure

Test report: 2724320

Test results:


Parameter		Wet Swell (informative only)	Re-dry Swell / Rating	Requirements according NALFA for 24 h
Final Thickness Swell [mm]	Position 1	0,53	0,23	Not applicable
	Position 2-4	0,32	0,11	
Qualitative Rating Specimen 1/2		4/4	2/1	Fulfilled
Water Leakage		Not detected		Not applicable

Dresden, 18/08/2025



Head of laboratory





Engineer in charge